



TECHNICAL DATA SHEET

JOHN C. DOLPH COMPANY

P.O. Box 267
320 New Road
Monmouth Junction, NJ
08852

Ph: (732) 329-2333
Fax: (732) 329-1143
info@dolphs.com
www.dolphs.com

SYNTHITE® AC-43

CLEAR AIR DRYING VARNISH

PRODUCT DESCRIPTION

AC-43 is a high temperature; fast cure, air dry, modified polyester varnish. Perfect for dip or spray applications where a clean clear protective coating is needed over various electric apparatus.

FEATURES & BENEFITS

- Quick drying
- Heat resistant
- Acid and alkali resistant
- Toughness and flexibility
- Fast cure cycles
- UL Systems to 155°C
- Good penetration
- Solderable

TYPICAL APPLICATIONS

- Stator Windings
- Printed Circuit Boards
- Coils
- Resistors
- Transformers
- Capacitors

TYPICAL PROPERTIES

Physical

Appearance/Color	Clear/Amber
Density @ 77°F (25°C), Lbs/gal	7.0 –8.0
Viscosity @ 77°F (25° C), Brookfield Viscometer, cps	20 - 70
Film Build, mils/side, ASTM D-115	1 - 1.5
Flash Point, °F	54
Thinner (solvent)	T-200X
Air Drying Time on Copper Strip, ASTM D-115, Min.	Set to Touch Tack Free
VOC Content, ASTM D 6053, lbs/gal	4.3
Corrosive Effect on Copper	None

All statements, technical information and recommendations related to Sellers' products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before using the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liabilities whatsoever in connection with such use. The statements contained herein are made in lieu of all warranties, expressed or implied. Seller shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or inability to use its products. The sole liability of John C. Dolph Co., Inc. for any claims arising out of the manufacture, use or sale of its products shall be for the buyer's purchase price.

Electrical

Dielectric Strength, ASTM D115, volts/mil	Dry	2,000
	Wet	1200

Chemical Resistance

Water	Excellent
Acid (10% Sulfuric Acid)	Excellent
Alkali (1% Sodium Hydroxide)	Excellent
Salt Water	Excellent
Oil, ASTM D-115	Passed

Thermal Class (UL-1446)

Twisted Pair	MW-24	155
	MW-28	130
	MW-35	180

APPLICATION GUIDELINES

AC-43 may be applied by brushing, dipping or spray. It will air dry in one hour but can be baked to improve its chemical and oil resistance. A 10-15 minutes bake at 300°F will provide a film with optimum toughness and bond strength.

For fast conveyor operation, the following cycle is recommended. We recommend that all ovens be preheated prior to the units being preheated and/or cured.

NOTE: AC-43 should be thinned 15% by volume for this type of cycle.

1. Preheat 10 minutes at 300°F.
2. Dip 15 seconds, or until bubbles have stopped.
3. Drain 45 seconds.
4. Bake 5 minutes at 330°F.

STORAGE AND SHELF LIFE

Shelf life is one year from date of shipment from our plant, when stored in closed containers at 70°F or below.

1. Store in cool, dry place at 70°F/21°C or below.
2. Protect from direct sunlight and sources of heat
3. Keep away from heat, sparks and open flame.

SAFETY AND ENVIRONMENT

Avoid contact with skin and eyes. See Material Safety Data Sheet

JCD/ds/AC43.9/03

AUTHORIZED DISTRIBUTOR