

Leading the Charge in Insulating Varnish

EL*600 CLEAR INSULATING VARNISH

EL*601
RED INSULATING VARNISH

EL®609 GREEN INSULATING VARNISH

- Meets performance requirements of ASTM D 115-07 4.2
- · Improved dielectric strength
- · Air Dries in 10 minutes
- Meets Class F Requirements
- · Resists Oils, Moisture, Acids and Alkalis



WHY CHOOSE SPRAYON® INDUSTRIAL INSULATING VARNISH?

Sprayon® Insulating Varnish is a coating with excellent insulating properties for impregnating and insulating electrical and electronic work. Excellent adhesion to metals, windings, coils. Air dries faster than most insulating materials. Protects surface against oils, moisture, acid and alkalis. Perfect for small field and magnet coils; penetrates oil and new windings; has excellent flexibility and water resistance. Can be used in a dip application and baked for faster cure rate and maximum hardness.

PROPERTIES

AEROSOL

RESIN TYPE: Epoxy / Phenolic **PROPELLANT:** Hydrocarbon Blend **APPEARANCE:** Available in red,

green & clear SHEEN: Semi-Gloss % SOLIDS: 22.83 WT./GAL.: 6.62 lb/gal SPECIFIC GRAVITY: 0.79 HAZARD CODE: 2, 4, 0

VOC: 55.17% **MIR:** .806

OTC & CALIFORNIA COMPLIANT:

*Yes

FLASH POINT: > 0°F

RECOMMENDED FILM THICKNESS:

1 Mil dft

COVERAGE PER AEROSOL (THEORETICAL): 10 SQ FT @ 1 MIL DFT

SHELF LIFE: 3 years from date of

manufacture

* ELECTRICAL AEROSOL COATINGS

ARE EXEMPT.



Aerorols are equipped with EZ TOUCH® Standard Nozzle for even coverage and improved comfort.



S00601000

S00600000

S00609000

WHY USE SPRAYON®?

MAXIMIZE THE PRODUCTIVITY AND SAFETY OF YOUR OPERATION.

THE HIGHEST PERFORMING MRO/INDUSTRIAL CHEMICALS AND LUBRICANTS NOW INTEGRATED WITH A NEW 5S VISUAL MANAGEMENT SYSTEM.



PROPERTIES

BULK

RESIN TYPE: Epoxy / Phenolic

APPEARANCE: Red SHEEN: Semi-Gloss

VISCOSITY: 60 KU @ 770F

% **SOLIDS:** 61.70 WT./GAL.: 9.12

SPECIFIC GRAVITY: 1.10 **HAZARD CODE:** 2, 3, 0 VOC: 418.31 g/l 3.49 lb/gal

MIR: .897

OTC & CALIFORNIA COMPLIANT: Yes

FLAMMABLE: Yes **FLASH POINT: 240F**

RECOMMENDED FILM THICKNESS: 1 Mil dft **COVERAGE PER GALLON (THEORETICAL):**

787 SQ FT @ 1 MIL DFT

SHELF LIFE: 3 years from date of manufacture.

PERFORMANCE

SPECIFICATION:

Meet performance requirements of ASTM D 115-07 4.2 Performance For:

4.2.1 Drainage: 22%

4.2.2 Time of Drying: See drying schedule

4.2.3 Build: 2.9 mm

4.2.8 Oil Resistance: See chemical resistance **TEMPERATURE CLASS:** Class F (155°C / 310°F)

DRY HEAT RESISTANCE:

Constant: 310°F Intermittently: 400°F

DILECTRIC STRENGTH: (ASTM D 115-07)

Red: 2,600 VPM Green: 2,890 VPM Clear: 2,300 VPM

ONE WEEK HARDNESS: (ASTM D 3363 SHORE

A 24 hr / 1 Week): 6B

FLEXIBILITY: (ASTM D 522) Pass

CHEMICAL RESISTANCE:

Aliphatic hydrocarbon solvents: Moderate Alkalis: Severe Aromatic hydrocarbon solvents: Severe Chlorinated solvents: Moderate Salt water: Severe Glycol ethers, alcohols: Severe Inorganic acids: Severe Organic acids: Severe Oils: Severe

DRYING SCHEDULE

DRYING TIME AEROSOL @ 70°F @ 50% R.H.:

To Touch: 10-15 Minutes

To handle: 30 Minutes (Tack Free)

Full cure: 7 Days

DRYING TIME BULK @ 70°F @ 50% R.H. 1mil wft:

To Touch: 10 Minutes

To handle: 1 Hour (Tack Free)

Full cure: 7 Days

NOTE: Curing can be accelerated by baking for

1 hr @ 300 degrees F **RECOAT:** Anytime

SURFACE PREPARATION

Must be applied directly to dry, clean surfaces and not over any other paint or coating. Proper surface preparation contributes to maximum service life of coatings. All contaminates (mill scale, rust, rust scale, chemicals, grease, oil, wax, weld spatter, old paint or other foreign matter must be removed down to

bare metal.



PRODUCT ID TAGS



SPRAYON® SYSTEM KANBAN TAGS



SPRAYON® SYSTEM **EDUCATIONAL POSTERS**



SPRAYON® SYSTEM MAGNETIC CAN HOLDERS



Visit SprayonSystem.com

EL™600 CLEAR INSULATING VARNISH

USFS

- Motor Windings
- · Field Coils
- Transformers
- Armatures
- · Commutator Ends
- Stater Windings
- · Ring and Frames
- · Bus Bars
- Sealing Electrical Switchboard Parts and Electronic Components



APPLICATION

DIRECTIONS FOR AEROSOL

Remove all rust, scale, paint, grease or foreign matter. A good clean surface is necessary. Apply directly to DRY surface and not over any other paint or coating. Product should be sprayed in a well-ventilated area. Use at room temperature (70°F.) for best operation. Turn can upside down. Hit sides lightly while rotating can in 1/4 turns until agitator ball breaks loose. While holding can upright, alternately shake the can up and down and in a circle for 30-60 seconds until the agitator travels freely in the bottom. NOTE: INSUFFICIENT MIXING **MAY CAUSE PLUGGING TO OCCUR.** Press spray button firmly with the can 8" to 12" away from surface being coated. Move can with short dusting strokes, releasing button at the end of each stroke. Apply several thin coats. To prevent clogging, hold can upside down and spray until only clear gas comes out.

DIRECTIONS FOR BULK

Brush, Dip or Spray. Remove all rust, scale, paint, grease or foreign matter. A good, clean surface is necessary. Apply directly to DRY surface and not over any other paint or coating. **NOTE: Bulk Separation is normal.** Mix thoroughly before and stir throughout project to maintain uniform resin to pigment suspension. Apply at full strength for most applications. Clean all equipment with acetone after use.

CLEAN UP: Acetone

SHIPPING

Refer to section 14 of the material safety data sheet for proper transport information and labeling.

RESOURCES

MSDS/EDS/PRODUCT DATA SHEETS: www.Sprayon.com CUSTOMER SERVICE: 1-800-777-2966 TECHNICAL INFORMATION: 1-800-251-2486

Sprayon Sku	UPC	Description	Quantity	Length	Width	Height
S00601000	0-75577-84213-1	Red	12	12.75	10.37	14.25
S00609000	0-75577-84215-5	Green	12	12.00	10.00	13.75
S00600000	0-75577-84214-8	Clear	12	12.00	10.00	13.75
A60110000	0-75577-84842-3	Red, 1 Gal.	4	12.25	12.37	12.50





©2010 Sprayon® Products Made in U.S.A.

Distributed by:

PRESERVE. PROTECT. PREVENT.™



Sprayon® Products 101 Prospect Ave. NW Cleveland, OH 44115 www.Sprayon.com 1-800-777-2966